

Mesoporous Pseudo Boehmite

GH-PB-QZ

This Pseudo Boehmite has middle-large pore volume This is one of our most widely used raw material of alumina catalyst carrier.

Highlight:

- >Relatively Economical
- >Popular as raw material of alumina catalyst carrier
- >Generally chosen by customers

Parameter	Value
SiO ₂	0.005-0.015%
Fe ₂ O ₃	0.005-0.015%
Na ₂ O	0.03-0.1%
Pore Volume	0.68-0.75ml/g
Surface Area	260-300 m ² /g
Dry Basis	≥68%

◆ For more information or place an order:

Jasmine Li
General Manager Assistant
**Shandong GuangHui New
Material Technology Co.,
Ltd**
All About Alumina

Mobile/Whats app/Wechat/
+86-18905338221
Fax/Tel: +86-533-3591884
Email:jasmine.li@ghnewmaterial.com
English Web: www.ghnewmaterial.com
Chinese Web: www.ghnewmaterial.cn