

## Macroporous Low Sulfur Pseudo Boehmite

### GH-PB-LXD

This Pseudo Boehmite has large pore volume and low sulfur content. This is one of our most widely used raw material of alumina catalyst carrier.

#### Highlight:

- >Low Sulfur Content
- >Large Pore Volume
- >Popular as raw material of alumina catalyst carrier
- > excellent feedback from customers

Parameter	Value
SiO <sub>2</sub>	0.01-0.03%
Fe <sub>2</sub> O <sub>3</sub>	0.008-0.012%
Na <sub>2</sub> O	0.03-0.05%
Sulfur	≤0.01%
Pore Volume	0.9-1.1ml/g
Surface Area	270-300 m <sup>2</sup> /g
Pore Diameter	10-15 nm
Dry Basis	≥68%
TBD	0.2-0.3 kg/L

#### ◆ For more information or place an order:

**Jasmine Li**

General Manager Assistant

**Shandong GuangHui New  
Material Technology Co.,  
Ltd**

**All About Alumina**

Mobile/Whats app/Wechat/:

+86-18905338221

Fax/Tel: +86-533-3591884

Email:jasmine.li@ghnewmaterial.com

English Web: www.ghnewmaterial.com

Chinese Web: www.ghnewmaterial.cn