

## **GH-PB-YT262 Microporous pseudo boehmite**

This Pseudo Boehmite has large demand quantity, and is widely used as raw material of multiple alumina catalyst carrier types. YT262 is also one of main raw material of our self-produced alumina catalyst carrier.

<b>Parameter</b>	<b>Value</b>
<b>Pore Volume ml/g</b>	0.3-0.5
<b>Surface Area m<sup>2</sup>/g</b>	250-280
<b>LOI (%)</b>	34-40
<b>SiO<sub>2</sub> (%)</b>	0.05-0.2
<b>Fe<sub>2</sub>O<sub>3</sub> (%)</b>	0.01-0.03
<b>Na<sub>2</sub>O (%)</b>	0.15-0.3
<b>Peptizing Index(%)</b>	95-98